

Quality	430									
According to Standard	ASTM A 276 - 06									
Number	-									
 KRANTI INDUSTRIAL METAL SUPPLIER LLP										
Comparable Standards	EN	W.N.	BS							
	X6Cr17	1.4016	430S15							
Chemical Analysis	C %	Mn %	Si %	P%	Cr %	Ni %	Mo %	S%	Other Elements	
	0.12	1.00	1.00	0.040 max.	16.0 to 18.0	—	—	0.030 max.	—	
Hot Work and Heat Treatment										
	Type ^A	Heat Treatment Temperature ^B °F (°C), min	Quench ant	Hardnes s HRC, min						
	—	—	—	—						
Mechanical Properties at Room Temperature										
Finish	Condition	Diameter or Thickness in. (mm)	Tensile Strength, min		Yield Strength, ^A		Elongation in 2 in. (50 mm) ^B		Reduction of Area, min, %	Brinell Hardness, max
		over 1 1/2 (38.10) to 1 3/4 (44.45)	ksi	Mpa	ksi	Mpa	or 4D min ⁰ %			
			125	860	100	690	18	45	-	
Hot Finished or Cold Finished	A	all	60	415	30	207	20	45	-	