

Quality	S2						
According to Standard	ASTM A 681						
Number	-						
 KRANTI INDUSTRIAL METAL SUPPLIER LLP							
Comparable Standards	EN	W.N.	AISI	DIN	UNS		
	-	1.2510	-	100MnCrW4	T41902		
Chemical Analysis	C %	Mn %	Si %	Cr %	V %	Mo %	S%
	0.40 to 0.55	0.30 to 0.50	0.90 to 1.20	-	0.50 max.	0.30 to 0.60	0.030 max.
	P %	W %					
	0.030 max.	-					
Hot Work and Heat Treatment							
	Preheat Treatment °F (°C)	Austenitizing Temperature, °F (°C) Salt Bath	Controlled Atmosphere Furnaces	Austenitizing Time (minutes)	Quench Medium	Tempering Temperature , °F (°C)	Minimum Hardness, RC
	1250 (677)	1625 (885)	1650 (899)	5 - 15	Brine	400 (204)	58
Mechanical Properties at Room Temperature							
Condition	Ø mm.	Rp0,2 min. N/mm2	Rm N/mm2	A min. %	KV min. J	Max. Brinell Hardness Annealed BHN	Max. Brinell Hardness Cold Drawn BHN
	-	-	-	-	-	217	241